

**DeWitt Company, Inc.**  
**Contractor Select Specifications**  
**A TYPAR® PRODUCT**

**TYPAR® is a registered trademark of Fiberweb, Inc.**

Typical Properties

Tensile Strength (lbs)	73
Elongation at Break (%)	>70
Puncture Strength (lbs)	23
Trap Tear (lbs)	35
Air Permeability (cm/sec)	$10 \times 10^{-2}$
Permittivity (sec <sup>-1</sup> )	3.0
Flux (Flow rate)	200 gal/sqft/min

Date: 03/17/09. This data sheet supersedes all previously issued data.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPILED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.