

DeWitt Company, Inc.
N-Sulate Specifications

<u>Typical Properties</u>	<u>Test Method</u>	
Weight		1.5 oz sqyd
Thickness	ASTM D-1910	11.5 mils
Tensile	ASTM D-1682	MD 35.9 lbs CD 27.1 lbs
Elongation		MD 120.0% CD 135.0%
Trapezoidal Tear	ASTM D-2263	<u>average</u> MD 10.8 CD 7.6
Air Permeability (Cu. ft ² /min)	ASTM D-737-75	420.0
Mullen Burst (psi)	ASTM D-3786-80A	61.0
Color		White

Date: 01/02/00. This data sheet supersedes all previously issued data.

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is to the best of our knowledge and belief, accurate and reliable as of the date compiled, however, no representation, warranty or guarantee is made as to its accuracy, reliability or completeness. It is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. We do not accept liability for any loss or damage that may occur from the use of this information nor do we offer any warranty against patent infringement.