

DeWitt Company, Inc.
Shady Dog Specifications

<u>Property</u>	<u>Test Method</u>	<u>Units</u>	<u>Value</u>
<u>Black</u>			
Weight	ASTM D-3776	OZ/SQYD	2.53
Breaking Strength (Grab Method)	ASTM D-5034	lbs	Warp – 54 Fill – 38
Breaking Elongation (Grab Method)	ASTM D-5034	%	Warp – 30 Fill – 126
Trapezoid Tear Strength	ASTM D-5587 (Opt. #1)	lbs	Warp – 32 Fill – 22
Burst Strength	ASTM D-3786	PSI	73
<u>Green</u>			
Weight	ASTM D-3776	OZ/SQYD	3.42
Breaking Strength (Grab Method)	ASTM D-5034	lbs	Warp – 58 Fill – 110
Breaking Elongation (Grab Method)	ASTM D-5034	%	Warp – 43 Fill – 59
Trapezoid Tear Strength	ASTM D-5587 (Opt. #1)	lbs	Warp – 43 Fill – 59
Burst Strength	ASTM D-3786	PSI	146

Date: 04-28-03. This data sheet supersedes all previously issued data.
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.