

## **DeWitt Company, Inc.** **15-Year Specifications**

### Typical Properties

### Test Method

• Material		Polypropylene Circular
• Color		Black with orange stripe
• Construction		10 x 10 Ultrasonic
• Weight (oz/SY)	ASTM D-3776	2
• Tensile Strength (lbs)	ASTM D-4632	80 x 80
• Burst (psi)	ASTM D-3786	260
• Trapezoid Tear (lbs)	ASTM D-4533	65
• Puncture (lbs)	ASTM D-4833	55
• Water Permeability (Gal/min/SF)	ASTM D-4491	9
• Ultraviolet Exposure (% Retention in strength)	ASTM D-4355	>50% after 3000 Hrs.
• Thickness (mils)		0

Average deviation shall be +/- 10% of the above value.

Date: 08/01/06. This data sheet supersedes all previously issued data.  
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.