

DeWitt Company, Inc.
Clip-It, Repins, Edging Specification

<u>Property</u>	<u>ASTM Methods</u>	<u>Units</u>
Density	D-729	.032 lb/in ³ .09 g/cc
Tensile Strength	D-638	3000 psi 20700 KPa 210 Kg/cm ²
Flexural Modulus	D-790	120 Kpsi 830 MPa 8435 Kg/cm ²
Notched Izod Impact	D-256	12.0 ft-lb/in 640 J/M 64 Kg-cm/cm
Un-notched Izod Impact (-20 C)	D-256	35 ft-lb/in 2565 J/M 265 Kg-cm/cm
Falling Weight Impact		400+ in-lb 45+ J 460+ Kg-cm
HDT @ 66psi	D-648	185°F 85°C
Hardness Rockwell R	D-785	70

Date: 10/25/04. This data sheet supersedes all previously issued data.
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPILED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.