



Silt Fence 24 & 36
(11 – 36” and 48” Oak Stakes)

Property	Test Method	
Material		Polypropylene
Construction		Circular Woven
Weight	ASTM-D3766	2 oz/sqyd
Grab Tensile (lbs)	ASTM-D4632	80 x 80
Burst (psi)	ASTM-D3756	190
Trapezoidal Tear	ASTM-D4533	60
Puncture (lbs)	ASTM-D4833	50
Water Permeability (gal/min/SF)	ASTM-D4491	9
Ultraviolet Exposure (% retention in strength)	ASTM-D4355	70% after 1600 hrs
Thickness		11.8 mil

Date: 4/25/18. This data sheet supersedes all previously issued data.
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILITY TO SATISFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.

905 South Kingshighway Sikeston, MO 63801 /
www.dewittcompany.com 573.472.0048 phone / 800.888.9669 /
573.471.6715 fax