DeWitt
DOWN TO EARTH PROTECTION

Product Specification Sheet

DNG120 Series Non-Woven Geotextile

DeWitt DNG120 is a 4.2 oz needlepunched non-woven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. The fabric resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids.

Properties	Test Method	Unit	Minimum Average Roll Value
Weight	ASTM D 5261	OZ/YD^2 ($G/M^{2)}$	4.2 (143)
Grab Tensile	ASTM D 4632	LBS	120
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	LBS	50
CBR Puncture Resistance	ASTM D 6241	LBS	340
Permittivity*	ASTM D 4491	SEC^{-1}	1.7
Water Flow*	ASTM D 4491	GPM/FT^2	120
AOS*	ASTM D 4751	US SIEVE	70
UV Resistance	ASTM D 4355	%/HRS	70/500

Primary Application : Soil Separation

*At the time of manufacturing. Handling may change these properties

Date: 06/01/23. This data sheet supersedes all previously issued data.
The above properties are typical averages.

THIS INFORMATION RELATES ONLY TO THE SPECIFIC MATERIAL DESIGNATED AND MAY NOT BE VALID FOR SUCH MATERIAL USED IN COMBINATION WITH ANY OTHER MATERIALS OR IN ANY PROCESS, SUCH INFORMATION IS TO THE BEST OF OUR KNOWLEDGE AND BELIEF, ACCURATE AND RELIABLE AS THE DATE COMPLIED. HOWEVER NO REPRESENTATION, WARRANTY OR GUARANTEE IS MADE AS TO ITS ACCURACY, RELIABILITY OR COMPLETENESS. IT IS THE USER'S RESPONSIBILTY TO SATISIFY HIMSELF AS TO THE SUITABILITY AND COMPLETENESS OF SUCH INFORMATION FOR HIS OWN PARTICULAR USE. WE DO NOT ACCEPT LIABILITY FOR ANY LOSS OR DAMAGE THAT MAY OCCUR FROM THE USE OF THIS INFORMATION NOR DO WE OFFER ANY WARRANTY AGAINST PATENT INFRINGEMENT.

905 South Kingshighway Sikeston, MO 63801
573.472.0048 phone • 800.888.9669 • 573.471.6715 fax • dewittcompany.com

DeWitt
DOWN TO EARTH PROTECTION